



SPECIFICATION SHEET – BLEACHED SOFTWOOD PULP

Raw Material

Pine	:100%
Fiber Length	:2.95 mm

Properties

ISO Brightness	:89,77
CIE Whiteness	:85,70

PFI REF.

SR°	0	3000	6000	6200
	12	18	37	40

Standard

ISO 2470
ISO 11476

ISO 5264-1
ISO 5267-2




Physical Properties 40

SR°

Grammage (g/m ²)	:84,27
Thickness (mm)	:0,112
Density (kg/m ³)	:750
Tensile Index (N·m/g)	:91,03
Breaking Length (km)	:9,282
Extension At Break (%)	:3,37
Bursting Index (kPa·m ² /g)	:6,37
Tearing Index (mN·m ² /g)	:11,63
pH	:7.2
Dirt Content	:0,1-1,0m ²

Standard

ISO 536
ISO 534
ISO 534
ISO 1924-3
ISO 1924-3
ISO 1924-3
ISO 2758
ISO 1974



Cellulose is produced in sheets measuring 70 x 84 cm. Bale size 70x84x42.5 cm...diameter 2.3 mm...(weight up to 250 kg). The size of a pack of 8 bales is 148x84x170 cm...diameter 3,0 mm...(weight up to 2000 kg)