



BLEACHED HARDWOOD PULP

BLEACHED SULPHATE HARDWOOD KRAFT PULP

Raw Material

Pine	:100%
Fiber Length	:1.7mm

Properties

ISO Brightness	:86,97
CIE Whitess	:87,98
SR°	:60

Standard

ISO 2470
ISO 5267-2

Physical Properties 60

SR°

Grammage (g/m ²)	: 84,27
Thickness (mm)	: 0,112
Density (kg/m ³)	: 750
Tensile Index (N·m/g)	: 84
Breaking Length (km)	: 8,5
Extension At Break (%)	: 3,37
Bursting Index (kPa·m ² /g)	: 5,2
Tearing Index (mN·m ² /g)	: 7,4
pH	: 7,3
Dirt Content	: 0,1-1,0m ²

Standard

ISO 536
ISO 534
ISO 534
ISO 1924-3
ISO 1924-3
ISO 1924-3
ISO 2758
ISO 1974

